

Valox* Resin 357U Americas: COMMERCIAL

Unreinforced PBTP, UL94 V-0/5VA rated. Improved UV resistant version of VALOX 357. Nonblooming flame retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	490	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	490	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	840	kgf/cm ²	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	840	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	21000	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	117	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	326	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	54	cm-kgf/cm	ASTM D 256
Gardner, 23°C	442	cm-kgf	ASTM D 3029
Modified Gardner, 23°C	442	cm-kgf	ASTM D 3029
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.18E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.24E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Specific Volume	0.75	cm ³ /g	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176.C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* Valox is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved

Valox* Resin 357U
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Mold Shrinkage, flow, 0.75-2.3 mm	0.8 - 1.1	%	SABIC Method
Mold Shrinkage, flow, 2.3-4.6 mm	1 - 1.4	%	SABIC Method
Mold Shrinkage, xflow, 0.75-2.3 mm	0.9 - 1.3	%	SABIC Method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.2 - 1.6	%	SABIC Method
ELECTRICAL			
Volume Resistivity	>1.2E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	18.5	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	25.1	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	18.5	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.2	-	ASTM D 150
Relative Permittivity, 1 MHz	3.2	-	ASTM D 150
Dissipation Factor, 100 Hz	0.003	-	ASTM D 150
Dissipation Factor, 1 MHz	0.03	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	0.45	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating (3)	0.63	mm	UL 94
UL Recognized, 94-5VA Rating (3)	2.99	mm	UL 94
Oxygen Index (LOI)	30	%	ASTM D 2863
UV-light, water exposure/immersion	F1	-	UL 746C

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* Valox is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved

Valox* Resin 357U
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	12	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	250 - 265	°C
Nozzle Temperature	245 - 260	°C
Front - Zone 3 Temperature	250 - 265	°C
Middle - Zone 2 Temperature	245 - 260	°C
Rear - Zone 1 Temperature	240 - 255	°C
Mold Temperature	50 - 75	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 100	rpm
Shot to Cylinder Size	40 - 80	%
Vent Depth	0.025 - 0.038	mm

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176.C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED. (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* Valox is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved